



www.palayeshparaffin.com
Info@palayeshparaffin.com

MEHR GOSTAR PARAFFIN

TEL:(+9821)88413268 88417249 88426089

ANALYSIS

Slack Wax

LIGHT SLACK WAX

Characteristics	SW05	SW12	Test Method
COLOR	white	white	IP-17 METHOD A 2CALL
KINEMATIC VISCOSITY @ 100°C	6cst~8cst	6cst~8cst	ASTM D 445
MELTING POINT	56 – 60°C	56 – 60°C	ASTM D 127
FLASH POINT	220~240 °C	220~240 °C	ASTM D 92
OIL CONTENT	5 - 8%	10 - 12%	*****

HEAVY SLACK WAX

Property	SW40	SW23	SW16	SW10	SW8	Test Method
COLOR	Yellowish Brown	Yellowish Brown	Yellowish Brown	Yellowish Brown	Yellowish Brown	
KINEMATIC VISCOSITY @°100 C	6cst- 8cst	6cst- 8cst	6cst- 8cst	6cst- 8cst	6cst- 8cst	ASTM D 445
MELTING POINT	62 – 66 ° C	62 – 66 ° C	62 – 66 ° C	62 – 66 ° C	62 – 66 ° C	ASTM D 127
FLASH POINT	220- 240 ° C	220- 240 ° C	220- 240 ° C	220- 240 ° C	220- 240 ° C	ASTM D 92
OIL CONTENT	% 40	%16-23	%12-16	%8 – 10	% 5 – 8	